

EZILINE Mortar Mix is a high performance product specifically designed for use in reinstating the field joints and repair of Tyco Water cement mortar lined steel pipes and fittings. It is a complete system, including the primer and mortar materials



### EZILINE – part A

- 20kg bag of premixed mortar
- Eliminates ordering sand and cement separately
- Meets Australian Standard
- Easy storage on site

### EZILINE – part B

- 5 litre container of liquid mix
- Easy to handle and store
- Eliminates decanting from larger drums
- Does not need water added
- A water reducing agent, strengthening agent, and bonding agent, when mixed with Part A
- Less waste

### EZILINE usage

Pipe OD	CML thickness	L*
mm	mm	mm
660	12	335
813	16	204
960	16	173
1085	16	153
1124	16	147
1219	16	136
1422	19	98
1626	19	86
1829	19	76

\*L = length of pipe that could be lined per EZILINE kit



### General application

Brush apply a prime coat of Part B [liquid] to cover the steel and adjacent mortar. Do not dilute.

Thoroughly manually mix Part A [do not use cement mixer] and as much of Part B required to form a stiff workable mixture. Do not add water.

Apply the mortar, compacting it into place to the level of the adjacent mortar.

**Note.** The working time reduces with temperature, and is approximately 20 minutes at 30°C.

### Technical data

#### Part A:

The dry mix includes a Type SR blended cement in full compliance with AS 3972 and sand in full compliance with AS 2758.1 classification C.

#### Part B:

The liquid is a high performance acrylic modifier.

#### Certifications:

Meets AS/NZS 4020 requirements for water contact.